

**ARDESIA A SPACCO**

<b>Peso specifico</b> <i>Specific weight</i>	2600 - 2900 Kg/m <sup>3</sup>
<b>Resistenza a flessione</b> <i>Bending strength</i> <b>(UNI EN 100)</b>	75 Newton / mm <sup>2</sup>
<b>Durezza alla scala Moss</b> <i>Hardness to Moss Scale</i> <b>(UNI EN 101)</b>	3
<b>Resistenza all'abrasione</b> <i>Abrasion resistance</i> <b>(UNI EN 102)</b>	1015 mm <sup>2</sup>
<b>Resistenza al gelo</b> <i>Frost resistance</i> <b>(UNI EN 202)</b>	<b>Ottima</b> <i>Very good</i>
<b>Resistenza allo scivolamento (BCR)</b> <i>Slip-proofing (BCR)</i>	<b>GA 1 Buona / Good</b> <b>GB 2 Buona / Good</b> <b>GA 3 Buona / Good</b>
<b>Analisi petrografica</b> <b>Petrographic description</b>	<b>Calcite</b> <b>Quarzo</b> <b>Mica</b> <b>Clorite</b> <b>Feldspati</b>

**I dati tecnici, provenienti dai cavaatori, possono presentare imprecisioni o essere incompleti, vanno quindi considerati puramente indicativi. La MARGRAF Spa non si assume nessuna responsabilità in merito.**

*The technical data is submitted in good faith and provided from what we feel are reliable sources. However, we in no way certify to the accuracy of this information as it may be incomplete or inaccurate. This information should be considered as indicative in nature. MARGRAF Spa assumes no responsibility for any of the technical data enclosed.*