

CALIZIA CAPRI

Peso specifico <i>Specific weight</i>	2700 kg/ m ³
Coefficiente di assorbimento <i>Absorption coefficient</i>	0,2 %
Porosità apparente <i>Apparent porosity</i>	0,5 %
Resistenza a compressione <i>Compressive strength</i>	857 kg/cm ²
Resistenza a compressione dopo congelamento <i>Compressive strength after freezing</i>	794 kg/cm ²
Resistenza a flessione <i>Bending strength</i>	1,71 kg/cm ³
Resistenza al consumo <i>Frictional wear Test</i>	2,58 mm
Resistenza all'impatto <i>Impact test</i>	30 cm
Descrizione macroscopica <i>Macroscopic description</i>	Pietra di grana fine e media, di colore bianco crema. <i>Limestone with fine or medium grain, creamy white colour.</i>
Descrizione microscopica <i>Microscopic description</i>	Accumulazione di fossile e intraclasto micritico in matrice esparitica. <i>Accumulation of fossil and micritic intraclasts in a sparitic matrix.</i>

I dati tecnici, provenienti dai cavaatori, possono presentare imprecisioni o essere incompleti, vanno quindi considerati puramente indicativi. La MARGRAF Spa non si assume nessuna responsabilità in merito.

The technical data is submitted in good faith and provided from what we feel are reliable sources. However, we in no way certify to the accuracy of this information as it may be incomplete or inaccurate. This information should be considered as indicative in nature. MARGRAF Spa assumes no responsibility for any of the technical data enclosed.