

GRIGIO TAO

Massa volumica reale <i>Real volume mass</i>	2710 Kg/m ³
Massa volumica apparente <i>Apparent volume mass</i>	2570 Kg/m ³
Porosità <i>Porosity</i>	5,19 %
Coefficiente di imbibizione (in peso) <i>Water absorption (by weight)</i>	0,76 %
Resistenza a compressione <i>Compressive strength</i>	<p>Condizione secca <i>Dry condition</i> 113,98 MPa</p> <p>Condizione satura <i>Saturated condition</i> 119,46 MPa</p> <p>Dopo congelazione <i>After freezing</i> 116,99 MPa</p>
Resistenza a flessione <i>Bending strength</i>	<p>Condizione secca <i>Dry condition</i> 25,22 MPa</p>
Analisi petrografica <i>Petrographic description</i>	Biointrapelmicrite <i>Packstone very fine calcarenite</i>

I dati tecnici, provenienti dai cavaatori, possono presentare imprecisioni o essere incompleti, vanno quindi considerati puramente indicativi. La MARGRAF Spa non si assume nessuna responsabilità in merito.

The technical data is submitted in good faith and provided from what we feel are reliable sources. However, we in no way certify to the accuracy of this information as it may be incomplete or inaccurate. This information should be considered as indicative in nature. MARGRAF Spa assumes no responsibility for any of the technical data enclosed.