

PIETRA PIASENTINA

Massa volumica apparente <i>Apparent volume mass</i>	2690 Kg/m ³
Assorbimento d'acqua <i>Water absorption</i>	0,21 %
Resistenza a compressione <i>Compressive strength</i>	145 MPa
Resistenza a compressione dopo gelività <i>Compressive strength after freezing</i>	144 MPa
Resistenza a flessione <i>Bending strength</i>	30 MPa
Microdurezza Knoop <i>Knoop micro-hardness</i>	1830 Mpa
Coefficiente di dilatazione lineare termica <i>Thermal linear dilatation coefficient</i>	6,6 X10 ⁻⁶ /°C

I dati tecnici, provenienti dai cavaatori, possono presentare imprecisioni o essere incompleti, vanno quindi considerati puramente indicativi. La MARGRAF Spa non si assume nessuna responsabilità in merito.

The technical data is submitted in good faith and provided from what we feel are reliable sources. However, we in no way certify to the accuracy of this information as it may be incomplete or inaccurate. This information should be considered as indicative in nature. MARGRAF Spa assumes no responsibility for any of the technical data enclosed.